



19×K19(SL)

钢丝绳公称直径 Nominal rope diameter		直径误差 Diameter tolerance		钢丝绳近似重量 Approximate unit Wt.		钢丝绳最小破断拉力 Minimum breaking force(Fmin,MBF)	
						公制单位/Metric unit	
		min.	max.			1960 Grade	2160 Grade
mm	inch	mm	mm	kg/100m	lb/ft	kN	kN
8		8.0	8.3	31.2	0.21	53.3	58.4
9		9.0	9.4	39.5	0.27	67.5	73.9
	3/8	9.5	9.9	44.6	0.30	75.2	82.31
10		10.0	10.4	48.8	0.33	86.3	94.6
	7/16	11.1	11.5	59.5	0.40	104.6	114.34
12		12.0	12.5	70.3	0.47	123.1	134.9
	1/2	12.7	13.2	78.9	0.53	138.4	151.27
13		13.0	13.5	82.5	0.55	147.7	161.7
14		14.0	14.6	95.6	0.64	171.3	187.6
	9/16	14.3	14.9	99.7	0.67	178.9	195.76
15		15.0	15.6	110.0	0.74	196.6	215.3
	5/8	15.9	16.5	125.0	0.84	220.0	241.15
16		16.0	16.6	125.0	0.84	220.2	241.2
18		18.0	18.7	158.0	1.06	276.5	302.8
19		19.0	19.8	176.0	1.18	310.9	340.6
	3/4	19.1	19.9	175.6	1.18	311.0	340.81
20		20.0	20.8	195.0	1.31	346.9	379.9
22		22.0	22.9	236.0	1.59	417.1	456.8
	7/8	22.2	23.1	241.1	1.62	424.9	465.39
24		24.0	25.0	281.0	1.89	499.1	546.7
25		25.0	26.0	305.0	2.05	540.1	591.5
	1	25.4	26.4	315.5	2.12	560.2	613.54
26		26.0	27.0	330.0	2.22	589.0	645.2
27		27.0	28.1	356.0	2.39	635.2	695.8
28		28.0	29.1	383.0	2.57	679.6	744.3
	1-1/8	28.6	29.7	398.8	2.68	708.6	776.83
29		29.0	30.2	410.0	2.76	729.0	798.4
30		30.0	31.2	439.0	2.95	777.2	851.3
31		31.0	32.2	469.0	3.15	829.9	909.0
	1-1/4	31.8	33.1	500.0	3.36	884.2	969.04
32		32.0	33.3	500.0	3.36	884.8	969.1
33		33.0	34.3	531.0	3.57	940.9	1030.6
34		34.0	35.4	564.0	3.79	998.2	1093.3
	1-3/8	34.9	36.3	598.3	4.02	1060.2	1162.13
35		35.0	36.4	598.0	4.02	1060.8	1161.9
36		36.0	37.4	632.0	4.25	1125.3	1232.6
38		38.0	39.5	705.0	4.74	1254.1	1373.7
	1-1/2	38.1	39.6	703.9	4.73	1253.1	1373.91
40		40.0	41.6	781.0	5.25	1363.6	1493.6

- | | | |
|---------------------|---|--|
| 交互捻
Regular Lay | × | 1. 35×K7(WA)是最适合用于高起升高度起吊的钢丝绳。
35×K7(WA) is the most suitable rope for high lifting height application. |
| 同向捻
Lang's Lay | ● | 2. 35×K7(WA)是阻旋转钢丝绳，并且外层股和内层股均压实。
35×K7(WA) is a rotation resistant rope, and made with compacted both parts of outer strands and inner strands |
| 压实股
Compacted | ● | 3. 35×K7(WA)具有相当高的破断拉力，并且对卷筒挤压有很强的抵抗力。
35×K7(WA) has an extremely high breaking strength with a very strong resistance against drum crushing |
| 旋锻
Rotary Swaged | × | |
| 塑料填充
PI | ● | 4. 35×K7(WA)钢丝绳有镀锌和光面两种，并且完全被完全润滑。
The rope is fully lubricated and made out of galvanized/ungalvanized wires |

www.wzwire.com

